



Chemical Resistant Data, % Weight Gain		
Sample	3 Days	28 Days
Deionized water	0.52	1.55
Methanol	9.38	7.16
Ethanol	2.41	6.92
Toluene	0.05	2.26
Xylene	0.02	0.20
Butyl Cellosolve	0.56	2.41
Methyl Ethyl Ketone (MEK)	17.17	Destroyed after 28 Days
10% Lactic Acid	0.76	2.99
10% Acetic Acid	1.70	5.64
70% Sulfuric Acid	0.01	0.36
50% Sodium Hydroxide	0.05	0.09
10% Sodium Hypochlorite	0.49	1.16
1, 1, 1 Trichloroethane	0.02	0.64